



*Stehlin Hostag Ink U.K. Ltd  
Unit D4, Linkmel Close, Longwall Avenue,  
Queens Drive Industrial Estate,  
Nottingham. NG2 1NA  
Tel: 0115 986 0477  
Fax: 0115 986 2681*

Date of Issue: 10/10/02

TDS 5/009

## **UV MATT LACQUER 3601**

Stehlin Hostag Ink UK Ltd are in partnership with Schmid Rhyner AG who have many years experience in print finishing and are the leading producer in Europe of overprint primers and UV varnishes. Schmid Rhyner through Stehlin Hostag will be able to provide you with the most technologically advanced waterbased primer and UV lacquer or varnish system in today's markets, giving you greater flexibility and productivity. All Schmid Rhyner products meet the latest stringent European legislation with regards to raw material selection.

With a wide and exciting range of products available we recommend you contact our laboratories at time of ordering to review all the technical requirements for you preferred application.

Schmid Rhyner Wessco UV Matt Lacquers exhibit the following properties:

- High reactivity
- Good slip
- Scuff resistance
- Scratch resistance
- Chemical resistance
- Die cutability
- Embossability
- Low odour
- High Flexibility

### Recommendations

- Use only coated paper and board with low absorbency and condition for at least 12 hours in the production room
- After printing let stack rest for 12 hours
- Use solvent and alkali resistant inks
- Do not use ink with a high wax content
- Consult ink supplier before using metallic inks



*Stehlin Hostag Ink U.K. Ltd  
Unit D4, Linkmel Close, Longwall Avenue,  
Queens Drive Industrial Estate,  
Nottingham. NG2 1NA  
Tel: 0115 986 0477  
Fax: 0115 986 2681*

Date of Issue: 10/10/02  
Cont/d... (sheet two)

TDS 5/009

- Do not use excess spray powder
- UV-High speed curing inks
- UV-lamps – minimum capacity 80w/cm
- Machine speeds dependant on substrate amount of power and condition of the UV lamps
- Application – Rollercoat System
- Anilox System
- Cleaning – ensure machine is clean after use

**Labelling**      Irritant (Xi)

**Storage**        In original closed container for 6 months at 10-25°C  
***Important Note – Stir well before use***

**Packaging**    25kg container  
                  200kg container  
                  1000kg container

#### **Printing Auxiliaries**

Delta UV Premium Wash	D1014
Delta Wash UV2	D1013

#### **Please Note**

***For double coater systems we recommend using Galacryl Waterbased Primer 8217***