



*Stehlin Hostag Ink U.K. Ltd  
Unit D4, Linkmel Close, Longwall Avenue,  
Queens Drive Industrial Estate,  
Nottingham. NG2 1NA  
Tel: 0115 986 0477  
Fax: 0115 986 2681*

Date of Issue: 15/11/02

TDS 7\008

## **ACRYLAC WATERBASED COATING SATIN ANILOX AC607/30**

AC607/30 is a high quality product formulated to give a smooth and streak free finish over heavy solids and silvers. It has been specifically developed for use through an anilox chamber roller system. It is suitable for both single and double sided application on commercial and carton work. The quick drying speed allows the coating to give good rub and scuff properties.

### General Characteristics

|                                 |             |
|---------------------------------|-------------|
| Gloss Level:                    | Satin       |
| Drying:                         | Fast        |
| Rub Resistance:                 | Medium/High |
| Suitable for Glueing:           | Yes         |
| Suitable for Hot Foil Stamping: | Yes         |
| Slip:                           | Medium      |
| Work/Turn:                      | Yes         |

### Technical Data

|                        |   |
|------------------------|---|
| Viscosity supplied at: | 29/32 sec. (DIN 4 at 20°C)  |
| Diluent:               | Water (1% to 10 sec reduction. Approx)                              |
| pH:                    | 7.8 – 8.5   |
| Drying Method:         | Combination of hot and cold air knives with a limited amount of IR. |

### Application

AC607/30 is suitable for application via the majority of conventional in-line dedicated anilox coating units.

### Special Precautions

Printing inks should be suitable, alkaline and alcohol resistant. Protect against frost and temperatures above 35°C (sunlight, radiators, etc).

Cont/d....



*Stehlin Hostag Ink U.K. Ltd  
Unit D4, Linkmel Close, Longwall Avenue,  
Queens Drive Industrial Estate,  
Nottingham. NG2 1NA  
Tel: 0115 986 0477  
Fax: 0115 986 2681*

Date of Issue: 15/11/02  
(sheet two)

TDS 7\008

To establish the suitability for glueing and hot foil stamping, a proof should be carried out before a full-scale production run. Clean coating unit with water or for dried on coating use Delta Emulsion Cleaner D1024. Wipe up all spillage.

Please refer to our Health and Safety Data sheets.

#### Packaging

Supplied in 25kg or 125kg drum or 1000kg silo